

Base Oil SN 500

www.ishtarcompany.com

Specification	Test Method	Min	Typical	Max
Kinematic Viscosity _c @40°C (cSt)	ASTM D-445	-	96	-
Kinematic Viscosity _c @100°C (cSt)	ASTM D-445	10.2	-	11.5
Viscosity Index	ASTM D-2270	-	95	-
Flash Point (COC) °C	ASTM D-92	230	-	-
Pour Point (COC) °C	ASTM D-97	-	-	-6
Carbon Residue (Conradson)Wt%	ASTM D-189	-	0.08	0.15
Total Acid Number mgKOH/g	ASTM D-664	-	-	0.05
Demulsibility	ASTM D-1401	-	Pass	-
Sulfate Content	ASTM D-1552	0.15	0.7	-
Color	ASTM D-1500	-	2.5	-
Density @15°C	ASTM D-4052	-	885	-
Copper Corrosion (3hrs@ 1000 °C)	ASTM D-130	-	-	1A
Foam ml	ASTM D-892	-	Nil	-